

## Technical Data Sheet

# SO GREEN

## 8MM CARPET UNDERLAY

Polyurethane Rebond  
 Suitable for stretch-fit installation of carpets

### Standard Specifications

Nominal density <sup>†</sup>	80 kg/m <sup>3</sup>
Nominal square weight <sup>†</sup>	870 g/m <sup>2</sup>
Nominal roll weight <sup>†</sup>	13.1 kg
Roll area*	15.07m <sup>2</sup> (1.37m x 11.0m)

### BS 5808: 1991

End Use Classification	GD/U, General Domestic Use
Nominal thickness	8.00 mm BS 4051
Work of compression Minimum 50 J/m <sup>2</sup>	>120 J/m <sup>2</sup> BS 4098 & BS 4052
Retention of work of compression (min 40%)	>70 % BS 4098 & BS 4052
Loss in thickness after dynamic loading (max 15%)	<10 % BS 4052
Loss in thickness after static loading (max 15%)	<10 % BS 4939
Resistance to cracking (not greater than 50mm)	Pass BS 5808
Breaking strength (length/width) min. 40N	>70N / >40N BS 2576
Extension under force (length/width) max. 10% @ 40N	<10% / <10%

### Flammability

Hot metal nut test (tested in Interfloor laboratory)	Medium radius of effects of ignition	BS 4790 & BS 5287
--	--------------------------------------	-------------------

### Other Specifications

Odour	No objectionable odour	
Colour / backing	Plain / printed nonwoven backing	
Packaging	Green film with black print	
Thermal resistance	2.32 togs <sup>†</sup>	BS 4745
Impact sound reduction (Delta Lw)	34 dB <sup>†</sup>	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions	Meets low VOC emission criteria	US Carpet & Rug Institute


### Notes

\* The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

<sup>†</sup> ±10%

<sup>‡</sup> Value derived from similar product test results

### Packaging



### Certification



### Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.